

bastion



Nitrile Soft Blue Powder Free Gloves



Ultimate solutions in hand protection

Nitrile Soft Blue Powder Free Gloves

| | |
|-------------------|--------------------------------------|
| Product: | Nitrile Soft Blue Powder Free Gloves |
| Material: | Nitrile - Latex Free |
| Type: | Non Sterile |
| Design: | Ambidextrous |
| Feature: | Micro Textured Fingers |
| Cuff: | Beaded |
| Usage: | Single Use only |
| Colour: | Ice Blue |
| Packaging: | 100 pcs/inner, 10 inners/carton |

Dimensions:

| Code | Size | Palm Width (mm) | MGM Length (mm) |
|---------|------|-----------------|-----------------|
| BNG7831 | XS | 70 - 79 | Min. 240 |
| BNG7832 | S | 80 - 89 | Min. 240 |
| BNG7833 | M | 90 - 99 | Min. 240 |
| BNG7834 | L | 100 - 109 | Min. 240 |
| BNG7835 | XL | 110 - 119 | Min. 240 |

Thickness:

| Location of Thickness Measurement | Single Wall (mm) |
|-----------------------------------|------------------|
| Finger | Min. 0.14 |
| Palm | Min. 0.09 |
| Cuff | Min. 0.05 |

Physical Properties:

| | Before Aging | After Aging |
|------------------------|--------------|-------------|
| Tensile Strength (MPa) | Min. 14 | Min. 14 |
| Elongation (%) | Min. 500 | Min. 400 |

This glove is suitable for use with Chemotherapy drugs as below

| Test Chemotherapy Drugs | Minimum Breakthrough Detection Time (Specimen 112/3)(Minutes) |
|---|---|
| Carmustine (BCNU), 3.3 mg/ml (3,300 ppm) | 0.3 |
| Cisplatin, 1.0 mg/ml (1,000 ppm) | >240 |
| Cyclophosphamide (Cytoxan), 20 mg/ml (20,000 ppm) | >240 |
| Dacarbazine (DTIC), 10.0 mg/ml (10,000 ppm) | >240 |
| Doxorubicin Hydrochloride, 2.0 mg/ml (2,000 ppm) | >240 |
| Etoposide (Toposar), 20.0 mg/ml (20,000 ppm) | >240 |
| Fluorouracil, 50.0 mg/ml (50,000 ppm) | >240 |
| Methotrexate, 25 mg/ml (25,000 ppm) | >240 |
| Mitomycin C, 0.5 mg/ml (500 ppm) | >240 |
| Paclitaxel (Taxol), 6.0 mg/ml (6,000 ppm) | >240 |
| Thiotepa, (THT) 10.0 mg/ml (10,000 ppm) | 16.0 |
| Vincristine, 1.0mg/ml (1,000 ppm) | >240 |
| Ifosfamide, 50.0 mg/ml (50,000 ppm) | >240 |

These gloves are manufactured under EN ISO13485 and ISO9001 Quality Systems



ARTG
174353



ASTM
D6319

EN374
EN455

