



# bastion



Nitrile  SuperTouch™ Long Cuff Powder Free Gloves



Ultimate solutions in hand protection

# Nitrile SuperTouch™ Long Cuff Powder Free Gloves

Product:	Nitrile SuperTouch Long Cuff Powder Free Gloves
Material:	Nitrile
Type:	Non Sterile
Design:	Ambidextrous
Feature:	Fully Micro Textured
Cuff:	Beaded
Usage:	Single Use only
Colour:	Blue
Packaging:	100 pcs/inner, 10 inners/carton

## Dimensions:

Code	Size	Palm Width (mm)	MGM Length (mm)
BNG7932	S	80 - 89	Min. 290
BNG7933	M	90 - 99	Min. 290
BNG7934	L	100 - 109	Min. 290
BNG7935	XL	110 - 119	Min. 290

## Thickness:

Location of Thickness Measurement	Single Wall (mm)
Finger	Min. 0.15
Palm	Min. 0.12
Cuff	Min. 0.08

## Physical Properties:

	Before Aging	After Aging
Tensile Strength (MPa)	Min. 14	Min. 14
Elongation (%)	Min. 500	Min. 400

## This glove is suitable for use with Chemotherapy drugs as below

Test Chemotherapy Drugs	Minimum Breakthrough Detection Time (Specimen 112/3) (Minutes)
Carmustine (BCNU), 3.3 mg/ml (3,300 ppm)	24.6 (24.6,27.7,26.9)
Cisplatin, 1.0 mg/ml (1,000 ppm)	>240
Cyclophosphamide (Cytoxan), 20 mg/ml (20,000 ppm)	>240
Dacarbazine (DTIC), 10.0 mg/ml (10,000 ppm)	>240
Doxorubicin Hydrochloride, 2.0 mg/ml (2,000 ppm)	>240
Etoposide (Toposar), 20.0 mg/ml (20,000 ppm)	>240
Fluorouracil, 50.0 mg/ml (50,000 ppm)	>240
Methotrexate, 25 mg/ml (25,000 ppm)	>240
Mitomycin C, 0.5 mg/ml (500 ppm)	>240
Paclitaxel (Taxol), 6.0 mg/ml (6,000 ppm)	>240
Thiotepa, (THT) 10.0 mg/ml (10,000 ppm)	68.9 (76.6,97.6,68.9)
Vincristine, 1.0mg/ml (1,000 ppm)	>240
Fentanyl Citrate Injection, 100mcg/2ml	>240

Test results provided in accordance with ASTM D 6978 by Akron Rubber Development Laboratory Inc. – Akron, Ohio 44305



ARTG 174353



ASTM D6319

EN374  
EN455